

ACE-56153

MATERIAL	% TML	% CVCM	CURE TIME	CURE TEMP	AT- MOS	% WVR	DATA REF	APPLICATION	MFR CODE
CEA 153 A/B AS 100/6.5 PBW SILVER FILLED EPOXY	0.29	0.01	1H	71	AIR	0.14	GSC18814	SHIELDING	IPN
CEA 153 A/B AS 100/6.5 PBW SILVER FILLED EPOXY	0.39	0.01	24H	25	AIR	0.28	GSC18867	SHIELDING	IPN
CEA 154 ONE PART ELEC COND EPOXY	0.54	0.01	2H	121	AIR	0.32	GSC18835	COND ADHESIVE	IPN